IN THE CLAIMS:

Amend the claims as follows:

Claim 1 (Currently amended): A flame-sprayed aluminum-alloy, containing from 12

to 60% by weight of Si, the balance being essentially AI, the aluminum-alloy flame-sprayed

by means of high velocity oxy-fuel flame-spraying method (HVOF) onto a substrate

roughened by shot blasting, and includes granular Si particles dispersed in the matrix of

the aluminum alloy, the granular Si particles having a short-diameter/long diameter ratio

of 1/3 or more and including granular Si particles having a particle size greater than 10 µm,

and further said flame-sprayed aluminum alloy has a thickness of 10 to 500 µm and has

adhesive strength of film higher than that of a flame-sprayed Ni film, as measured by a

shear-fracture testing method.

Claim 2 (Currently amended): A flame-sprayed aluminum-alloy containing from 12

to 60% by weight of Si, from 0.1 to 30% by weight of Sn, the balance being essentially Al,

the aluminum-alloy flame-sprayed by means of high velocity oxy-fuel flame-spraying

method (HVOF) on a substrate roughened by shot blasting, and includes granular Si

particles and Sn dispersed in the matrix of the aluminum alloy, the granular Si particles

having a short-diameter/long diameter ratio of 1/3 or more and including granular Si

particles having a particle size greater than 10 µm, and further said flame-sprayed

aluminum alloy has a thickness of 10 to 500 µm and has adhesive strength of film higher

2

Serial Number: 09/423,981

Response to Not. Appeal filed 826/03

Prel. Sub. filed 2/26/04

than that of a flame-sprayed Ni film, as measured by a shear-fracture testing method.

Claim 3 (Original): A flame-sprayed aluminum alloy according to claim 1 or 2,

wherein said alloy contains at least one element of the group consisting of: 7.0% by weight

or less of Cu; 5.0% by weight or less of Mg; 1.5% by weight or less of Mn; 1.5% by weight

or less of Fe; and 8.0% by weight or less of Ni.

Claim 4 (Original): A flame-sprayed aluminum alloy according to any one of claims

1 through 3, wherein the average particle diameter of said granular Si is 50 μ m or less.

Claim 5 (Canceled):

Claim 6 (Previously presented): A flame-sprayed aluminum-alloy according to claim

5, wherein a coating containing a material selected from the group consisting of Sn, Pb-Sn

and MoS₂-graphite is applied on said flame-sprayed aluminum alloy.

3